DRAWN DATE DN 05-25-94 CHECKED

E0961183

TRUCK, INC. 415 EAST DUNDEE OTTAWA, KANSAS 66067 FAX (913) 242-6117 (913) 242-2200

SHEET

1 of 1

APPROVED HK 08-28-96 ENGINEERING SPECIFICATION OR INSTRUCTIONS

ESN-0020

TOLERANCE

STANDARD SPECIFICATION FOR:

STRESSPROOF® 1144 SHAFTING ROUNDS ASTM A311, CLASS B

MECHANICAL PROPERTIES:

MIN. YIELD STRENGTH (PSI) = 100,000

MIN. TENSILE STRENGTH (PSI) = 125,000

% OF ELONGATION IN 2" = 10

% REDUCTION OF AREA = 30

HARDNESS = R_c 23/27

DIAMETER TOLERANCES:

DIAMETER

COLD DRAWN

DIAMETER	TOLERANCE
1.50 & UNDER	.000 TO004"
OVER 1.50 TO UNDER 2.50	.000 TO005"
2.50 TO 4.00	.000 TO006"
OVER 4.00 TO 6.00	.000 TO007"

TURN, GROUND & POLISHED

1.25 TO 1.50	0005 TO0015"
OVER 1.50 TO UNDER 2.50	−.0005 TO −.0020"
2.50 TO 3.00	−.0005 TO −.0025"
OVER 3.00 TO 4.00	−.0005 TO −.0035"
OVER 4.00 TO 6.00	−.0005 TO −.0040"
OVER 6"	0005 TO0045"

SURFACE FINISH: 8 TO 16 RMS

NOTE: DRAWING MUST STATE COLD DRAWN OR TURN GROUND & POLISHED